

PRODUCT DESCRIPTION

NCB is a fully formulated water-based acrylic product. It is a highly flexible and crack-resistant base and grout coat that is tintable to a wide variety of colors.



BASIC USES

- NCB is used as a base coat to embed reinforcing mesh in a Dryvit system.
- NCB is used as the grout coat for with the Custom Brick Finish System.
- NCB is used as the base coat for re-skimming existing lamina during repair and remediation

FEATURES & BENEFITS

FEATURE

- Ready to use right from pail
- Wet polymer modified
- Free of solvents
- Vapor permeable
- Highly flexible

BENEFIT

- No mixing/no cement equals less labor
- Excellent durability, adhesion
- Complies with VOC requirements
- Does not allow moisture buildup
- Better crack resistance

PROPERTIES

Working Time: When the NCB is contained in an open pail, there is no working time limit. Small amounts of water can be added continuously to the pail to adjust the workability. Partially used containers of NCB, when tightly sealed, may be used the next day.

Drying Time: NCB dries and develops physical properties by the evaporation of water. Drying time depends upon the air temperature, relative humidity and wind conditions. Under average drying conditions [70 °F (21 °C), 55% R.H.], NCB will be dry in 24 hours. Protect NCB from rain for at least 24 hours. Under adverse drying conditions (low temperature and high relative humidity), NCB should be protected until it is cured hard.

Testing Information: For individual test data on this product's properties, refer to the chart included with this document.

Application Procedure: For complete application instructions, refer to the appropriate Dryvit system application instructions.

Job Conditions: Air and surface temperature for the application of the NCB material must be 40 °F (4 °C) or higher and must remain so for a minimum of 24 hours. When used as a grout coat for Custom Brick finishes, air and surface temperature must be 55 °F (13 °C) or higher and must remain so for a minimum of 24 hours.

Temporary Protection: Shall be provided at all times until the adhesive, base coat, finish and installation of permanent flashings, sealants, etc. are completed to protect the wall from inclement weather and other sources of damage.

SURFACE PREPARATION

- **Base Coat:** NCB is intended for use in a Dryvit system. The insulation board shall be properly installed to an approved substrate using an approved Dryvit adhesive. The adhesive shall be properly cured, all EPS insulation board joints tightly butted, joints wider than 1/16 in (1.6 mm) slivered with insulation board to create a tight fit and the surface rasped to a smooth and level plane.

- **Grout Coat:** NCB may be used as the grout coat for the Custom Brick application. The base coat shall have cured a minimum of 24 hours and shall be dry, clean and free of any contaminants prior to applying the Custom Brick NCB Grout Coat.

MIXING

Mix NCB to a smooth, homogeneous consistency with a "Twister" paddle or equivalent mixing blade, powered by a 1/2 in (12.7 mm) drill, at 450-500 rpm. A small amount of clean, potable water may be added to adjust workability.

TINTING

NCB may be tinted to provide a colored base or grout coat. Ten standard colors and many custom colors are available.

APPLICATION

Base Coat: For base coat application, all insulation board irregularities greater than 1/16 in (1.6 mm) must be sanded flush. Apply the base coat to the entire surface of the insulation board. Fully embed the Dryvit reinforcing mesh in the wet base coat troweling from the center to the edge of the reinforcing mesh so as to avoid wrinkles. The reinforcing mesh shall be continuous at all corners and lapped or butted in accordance with Dryvit's recommendations. The overall minimum base coat thickness shall be sufficient to fully embed the reinforcing mesh. The recommended method is to apply the base coat in two applications. All areas requiring higher impact resistance shall be detailed on the plans and described in the contract documents. The products shall be installed in accordance with Dryvit's recommendations.

Grout Coat: Air temperature for application of NCB Grout must be between 55 °F (13 °C) and 100 °F (38 °C) and must remain so for 24 hours. With a stainless steel trowel, apply NCB Grout over the dry base coat. Apply the NCB Grout to a uniform thickness not exceeding 1/16 in (1.6 mm). Allow to dry a minimum of 24 hours prior to adhering custom Brick templates.

Skim Coat: Apply the NCB material over the entire surface of the existing finish in a uniform thickness [approximately 1/16 in (1.6 mm) thick]. When specified, fully embed the Dryvit reinforcing mesh as described in the base coat application previously.

COVERAGE

Approximately 110-130 ft² (10.2-12.1 m²) per 65 lb (29.5 kg) pail. Approximately 18.6-23.2 m² (200-250 ft²) when used as a grout.

STORAGE

NCB must be stored at a minimum of 40 °F (4 °C) and a maximum of 100 °F (38 °C) in tightly sealed containers protected from weather and out of direct sunlight.

The shelf life is 2 years from date of manufacture when properly stored in unopened pails.

CAUTIONS & LIMITATIONS

- Avoid applying NCB in direct sunlight. Always work on the shady side of the wall or protect the area with appropriate shading material.
- While drying, the NCB must not be exposed to the formation of dew on its surface. This could lead to localized delamination and the formation of blisters.
- Before applying Dryvit finish to the NCB base coat, insure that the surface is thoroughly and uniformly dry. Particular attention must be paid to areas of mesh overlap where the NCB is thicker and will take longer to dry. Application of finish to an incompletely dried base coat will result in mottled appearance.
- Do not use NCB as an adhesive.
- NCB is not recommended to embed reinforcing mesh at EPS edges that will receive sealant.

CLEAN UP

Clean tools with water while the NCB material is still wet.

TECHNICAL AND FIELD SERVICES

Available upon request.

TEST	TEST METHOD	CRITERIA	RESULTS
Surface Burning Characteristics	ASTM E 84	ICC and ANSI/EIMA 99-A-2001 Flame Spread <25 Smoke Developed <450	Passed
Water Vapor Transmission	ASTM E 96 Procedure B	ICC: Vapor Permeable No ANSI/EIMA Criteria	14.7 Perms
Accelerated Weathering	ASTM G 155 (Xenon Arc)	ICC: 2000 hours: No deleterious effects ¹	5000 hours: No deleterious effects ¹
Freeze-Thaw Resistance	ASTM E 2485/ICC-ES Proc: ICC ES (AC219*)	No deleterious effects ¹ after 10 cycles	Passed – No deleterious effects ¹ after 10 cycles
Water Resistance	ASTM D 2247	ICC and ANSI/EIMA 99-A-2001 14 days: No deleterious effects ¹	14 days: No deleterious effects ¹
Tensile Bond ²	ASTM C 297/E 2134 (formerly EIMA 101.03)	ICC and ANSI/EIMA 99-A-2001: Minimum 15 psi (104 kPa) – substrate or insulation failure	>15 psi (104 kPa)
Water Penetration	ASTM E 331	No water penetration beyond the inner-most plane of the wall after 15 minutes at 2.86 psf (137 Pa)	Passed
Ignitability	NFPA 268	No ignition at 12.5 kw/m ² at 20 minutes	Passed
Fire Resistance	ASTM E 119	No effect on the fire resistance of a rated wall assembly	Passed 1 hour and 2 hour
Intermediate Multi-Story Fire Test	NFPA 285 (UBC 26-9)	1. Resist flame propagation over the exterior surface 2. Resist vertical spread of flame within combustible core/component of panel from one story to the next 3. Resist vertical spread of flame over the interior surface from one story to the next 4. Resist lateral spread of flame from the compartment of fire origin to adjacent spaces	Passed

1. No cracking, checking, rusting, crazing, erosion, blistering, peeling, or delamination when viewed under 5x magnification.
2. Sample consists of NCB Base Coat applied over 1" EPS.

*AC219 – Acceptance Criteria for EIFS

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit products as of the date of publication of this document and is presented in good faith. Dryvit assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit.

For more information on Dryvit or Continuous Insulation, [click here](#).

Printed in USA. Issued 1.1.2022

©Dryvit 2022

DS402

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



dryvit.com | 800.556.7752



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com