



TECHNICAL DATA SHEET

STUCCOAT CRACK ISOLATION MEMBRANE

Dry Mix, Polymer-Modified, Cementitious,
Fiber-Reinforced Base Coat
DS1015

PRODUCT DESCRIPTION

High-performance, fiber-reinforced, dry mix, polymer-modified base coat specifically formulated for use with StucCoat One-Coat systems.

BASIC USES

StucCoat Crack Isolation Membrane is a base coat for the StucCoat One-Coat System. It may be used to embed StucCoat Standard Mesh over approved substrates.

FEATURES & BENEFITS

FEATURE

- Single component
- Dry polymer modified
- Smooth consistency
- Vapor permeable

BENEFIT

- Ready to use, just add water
- Excellent durability, adhesion
- Trowels easily thus more production
- Does not allow moisture buildup

PROPERTIES

Working Time: After mixing, the working time of the StucCoat Crack Isolation Membrane mixture is approximately 1 to 1 1/2 hours, depending on ambient weather conditions

Drying Time: Drying time of the StucCoat Crack Isolation Membrane mixture is dependent on the air temperature and relative humidity. Under average drying conditions [70 °F (21 °C), 55% R.H.], the StucCoat Crack Isolation Membrane mixture will dry in 24 hours. Protect work from rain for at least 24 hours. Being a cementitious product, the StucCoat Crack Isolation Membrane mixture develops full strength in 28 days.

Testing Information: For individual test data on this product's properties, refer to the chart included with this document.

Application Procedure: FOR COMPLETE INSTRUCTIONS, REFER TO THE APPROPRIATE DRYVIT APPLICATION INSTRUCTIONS.

Job Conditions: Air and surface temperatures for application of the StucCoat Crack Isolation Membrane mixture must be at 40 °F (4 °C) or higher and must remain so for a minimum of 24 hours.

Temporary Protection: Shall be provided at all times until the adhesive, base coat, finish, and installation of permanent flashings, sealants, etc. are completed to protect the wall from inclement weather and other sources of damage.

Acceptable Substrates:

- Dryvit StucCoat Plaster Systems

SURFACE PREPARATION

- Surfaces must be above 40 °F (4 °C) and must be clean, dry, structurally sound and free of efflorescence, grease, oil, form release agents and curing compounds.
 - The substrate shall be flat within 1/4 in (6.4 mm) in any 4 ft (1.2 m) radius.
-

MIXING

Pail Mixing: One 50 lb (22.7 kg) bag of StucCoat Crack Isolation Membrane will produce approximately 5 gal (19 L) of StucCoat Crack Isolation Membrane mixture. Add 6-7 qt (5.7 -6.6 L) of clean potable water into a clean plastic container. Add the StucCoat Crack Isolation Membrane slowly while constantly mixing with a "Twister" paddle or equivalent mixing blade, powered by a 1/2 in (12.7 mm) drill, at 500-1200 rpm. **NOTE: A minimum 7 amp drill works best for Portland cement based materials.** Thoroughly mix until uniformly wetted, adjusting consistency with a small amount of water or StucCoat Crack Isolation Membrane. Allow the material to set for 5-10 minutes then mix to break the initial set. Retemper, adding a small amount of water if necessary. Material must be free of lumps before using.

Mortar Mixer: Add 6-7 qt (5.7 -6.6 L) of clean potable water for each 50 lb (22.7 kg) bag of StucCoat Crack Isolation Membrane into a clean mortar mixer. Add the StucCoat Crack Isolation Membrane while the mixer is running. Let mix 3 to 5 minutes, shut the mixer off for 5-10 minutes, then run mixer for another 2 to 3 minutes to break the set adding a small amount of water if necessary to adjust workability. The pot life is 1 to 1 1/2 hours to break the initial set depending on weather.

APPLICATION

CAUTION: Do not install the StucCoat Crack Isolation Membrane mixture directly on the substrate. Immediately place the insulation board on the substrate, ensuring that no StucCoat Crack Isolation Membrane mixture gets into the board joints. Do not allow the StucCoat Crack Isolation Membrane mixture to form a skin before positioning the insulation board on the substrate, as it will affect the bond strength.

Crack Isolation Membrane: For crack isolation membrane application, all insulation board irregularities greater than 1/16 in (1.6 mm) must be sanded flush. Apply the base coat to the entire surface of the insulation board. Fully embed the StucCoat reinforcing mesh in the wet crack reinforcing membrane, troweling from the center to the edge of the reinforcing mesh so as to avoid wrinkles. The reinforcing mesh shall be continuous at all corners and lapped or butted in accordance with Dryvit's recommendations. The overall minimum crack isolation membrane thickness shall be sufficient to fully embed the reinforcing mesh. The recommended method is to apply the crack isolation membrane in two applications. All areas requiring higher impact resistance shall be detailed on the plans and described in the contract documents. The application shall be in accordance with Dryvit's recommendations.

PACKAGING

Base coat is supplied in 50 lb (22.67 kg) bags.

COVERAGE

Approximately 120 ft² (11.1 m²) per bag, depending on job conditions, application techniques, etc. This includes adhesive and base coat layers.

STORAGE

StucCoat Crack Isolation Membrane bags must be protected from moisture and weather. The bags shall be stored off the ground in a cool dry location out of direct sunlight. If the StucCoat Crack Isolation Membrane is warm or hot the pot life of the StucCoat Crack Isolation Membrane mixture will be reduced.

The shelf life is 1 year from date of manufacture when properly stored in unopened bags.

CAUTIONS & LIMITATIONS

- Avoid applying Genesis in direct sunlight. Always work on the shady side of the wall or protect the area with appropriate shading material.
- Clean cool potable water may be added to adjust workability. Do not overwater. Warm water will accelerate the set.
- Mixing paddles and pails must be clean. Contamination from previous mixing will lead to a short pot life.
- Wear protective eyewear and clothing since the product contains cement, which can cause irritation.

CLEAN UP

Clean tools with water while the StucCoat Crack Isolation Membrane mixture is still wet.

TECHNICAL AND FIELD SERVICES

Available on request.

GENESIS® DM Testing

TEST	TEST METHOD	CRITERIA	RESULTS
Surface Burning Characteristics	ASTM E 84	ICC and ANSI/EIMA 99-A-2001 Flame Spread <25 Smoke Developed <450	Passed
Water Vapor Transmission	ASTM E 96 Procedure B	ICC: Vapor Permeable No ANSI/EIMA Criteria	63 Perms
Accelerated Weathering	ASTM G 23 (Carbon Arc)	ICC: 2000 hours: No deleterious effects ¹	2000 hours: No deleterious effects ¹
Freeze-Thaw Resistance	ASTM E 2485 (formerly EIMA 101.01)	ANSI/EIMA 99-A-2001 60 cycles: No deleterious effects ¹	60 cycles: No deleterious effects ¹
	ASTM E 2485/ICC-ES Proc: ICC ES (AC219*)	No deleterious effects ¹ after 10 cycles	Passed – No deleterious effects ¹ after 10 cycles
Water Resistance	ASTM D 2247	ICC and ANSI/EIMA 99-A-2001 14 days: No deleterious effects ¹	14 days: No deleterious effects ¹
Tensile Bond ²	ASTM C 297/E 2134 (Formerly EIMA 101.03)	ICC and ANSI/EIMA 99-A-2001 Minimum 15 psi (104 kPa) – substrate or insulation failure	15 psi (104 kPa)
Water Penetration	ASTM E 331	No water penetration beyond the inner-most plane of the wall after 2 hours at 6.24 psf (299 Pa)	Passed
Ignitability	NFPA 268	No ignition at 12.5 kw/m ² at 20 minutes	Passed
Intermediate Multi-Story Fire Test	NFPA 285 (UBC 26-9)	<ol style="list-style-type: none">1. Resist flame propagation over the exterior surface2. Resist vertical spread of flame within combustible core/component of panel from one story to the next3. Resist lateral vertical spread of flame over the interior surface from one story to the next4. Resist lateral spread of flame from the compartment of fire origin to adjacent spaces	Passed

1.No cracking, checking, rusting, crazing, erosion, blistering, peeling, or delamination when viewed under 5x magnification.

2. Sample consists of 1" EPS adhered to various substrates

* AC219 – Acceptance Criteria for EIFS loss or damage.

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit products as of the date of publication of this document and is presented in good faith. Dryvit assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit.

For more information on Dryvit or Continuous Insulation, [click here](#).

Printed in USA. Issued 7.28.2023

©Dryvit 203

DS1015

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



dryvit.com | 800.556.7752



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com