




DRYVIT INSULATION COMPARISON



PROPERTY	EPS (Expanded Polystyrene)	GPS (Graphite Polystyrene)	XPS (Extruded Polystyrene)	MINERAL WOOL ROCKWOOL® Frontrock™
R-VALUE PER INCH	3.6 to 4.2	4.7 to 5.0	4.5 to 5.0	4.0 to 4.2
VAPOR PERMEABILITY	Moderate	Moderate	Low	High
COMBUSTIBILITY	Combustible (Class A Flame Spread)	Combustible (Class A Flame Spread)	Combustible (Class A Flame Spread)	Non-Combustible
MOISTURE RESISTANCE	Moderate	Moderate	High	Moderate
RECYCLED CONTENT	Low	Low	Low	High (up to 70%+)
DRYVIT SYSTEMS	- Outsulation® Plus MD - Outsulation® Plus MD + Securock® ExoAir® 430 - Outsulation® Plus MD + Fireblocking - Outsulation® MD, - Outsulation® MVS, - Outsulation® HDCI - Outsulation® HDCI + Securock® ExoAir® 430 - Outsulation® LCMD - Outsulation® Plus - Outsulation® RMD	- Outsulation® Plus MD - Outsulation® Plus MD + Securock® ExoAir® 430 - Outsulation® Plus MD + Fireblocking - Outsulation® X - Outsulation® X + Securock® ExoAir® 430	- Outsulation® X - Outsulation® X + Securock® ExoAir® 430	- Outsulation® Plus MD + Fireblocking - Outsulation® Mineral Wool - Outsulation® Mineral Wool + Securock® ExoAir® 430