



TECHNICAL DATA SHEET

WEATHERLASTIC®

Flexible, Elastomeric
Exterior Finishes
DS418

PRODUCT DESCRIPTION

Weatherlastic is a line of textured finishes that are 100% acrylic, utilizing DPR (Dirt Pickup Resistant) chemistry and an elastomeric binder to bridge hairline cracks. Weatherlastic is available in four distinct textures. Weatherlastic Quarzputz®, Weatherlastic Sandpebble®, Weatherlastic Sandpebble® Fine, Weatherlastic Adobe® and achieve textures which are governed by aggregate size as well as the trowel motion in finishing the wall. Quarzputz produces an open-textured pattern in a regular or random style, Sandpebble trowels to a pebble texture, Sandpebble Fine produces a fine pebble texture; Adobe trowels to a smooth, fine sand texture.



BASIC USES

Weatherlastic finishes are ideally suited as a protective and decorative coat over stucco, concrete, masonry, CMU and EIFS substrates.

FEATURES & BENEFITS

FEATURE:

- Elastomeric formulation
- Dirt Pickup Resistant
- Mildew Resistant
- Plasticizer Free
- Low temperature flexibility

BENEFIT:

- Bridges hairline cracks
- Wall stays cleaner longer
- Resists mildew longer
- More crack resistant
- Less likely to crack when it reaches a certain temperature

PROPERTIES

Drying Time: Drying of the Weatherlastic finish is dependent on the air temperature, relative humidity and thickness of finish. Under average drying conditions [70 °F (21 °C), 55% R.H.], protect work from rain for at least 24 hours.

Testing Information: For individual test data on this product's properties, please reference the chart included with this document.

Job Conditions: Air and surface temperature for application of Weatherlastic finishes must be 40 °F (4 °C) or higher and must remain so for a minimum of 48 hours.

Temporary Protection: Shall be provided at all times until the base coat, finish and permanent flashings, sealants, etc. are completed to protect the wall from weather and other damage.

SURFACE PREPARATION

Surfaces must not be below 40 °F (4 °C) and must be clean, dry, structurally sound and free of efflorescence, grease, oil, form release agents and curing compounds.

- **Concrete:** Shall have cured a minimum of 28 days prior to application of the coatings. If form release agents or curing compounds are present on the concrete surface, the surface shall be thoroughly washed with muriatic acid and flushed to remove residual acid. All projections shall be removed and small voids filled with Genesis® Primus®, Genesis® DM or Primus® DM mixture. Dryvit Weatherprime® shall be applied to the prepared concrete surface using a roller or brush.

- **Masonry:** The masonry surface, with joints struck flush, shall be "skim coated" with Genesis, Primus, Genesis DM or Primus DM mixture to produce a smooth, level surface.
- **Stucco:** Weatherlastic finishes shall be applied to the properly primed, cured brown coat. If additives are present in the stucco, a test patch shall be made and bond strength checked prior to application. If applied to existing stucco, one coat of Weatherprime should be applied to the brown coat before applying the Weatherlastic finish.

MIXING

Thoroughly mix Weatherlastic finishes with a Goldblatt Jiffler Mixer until a uniform workable consistency is attained.

APPLICATION

Thoroughly mix Weatherlastic finishes with a Goldblatt Jiffler Mixer until a uniform workable consistency is attained.

COVERAGE

All coverages are approximate and depend on substrate, details and individual application technique.

Weatherlastic Quarzputz: Approximately: 140 ft² (13 m²) per 70 lb (32 kg) pail. WFT 57.29 mils, DFT 42.0 mils. Vol Solids 73.32%.

Weatherlastic Sandpebble: Approximately 130 ft² (12 m²) per 70 lb (32 kg) pail. WFT 61.69 mils, DFT 44.2 mils. Vol Solids 71.68%.

Weatherlastic Sandpebble Fine: Approximately 150 ft² (14 m²) per 70 lb (32 kg) pail. WFT 53.47 mils, DFT 38.3 mils. Vol Solids 71.6%.

Weatherlastic Adobe: Approximately 190 ft² (18 m²) per 70 lb (32 kg) pail. WFT 42.21 mils, DFT 30.5 mils. Vol Solids 72.27%.

STORAGE

Weatherlastic finish must be stored at a minimum of 40 °F (4 °C) and a maximum of 100 °F in tightly sealed containers protected from weather and out of direct sunlight.

The shelf life is 2 years from date of manufacture when properly stored in unopened pails.

MAINTENANCE

Weatherlastic Finishes: Using a stainless steel trowel, apply a level coat of Weatherlastic finish to a uniform thickness slightly thicker than the largest aggregate. The texture is achieved by a uniform hand floating motion with a clean stainless steel trowel, plastic trowel or wood float. Apply light pressure in a circular motion. Maintain a wet edge for uniformity of color and texture.

CAUTIONS & LIMITATIONS

- Weatherlastic finish must not be used on exposed exterior horizontal surfaces. Minimum slope is 6 in 12 which is (27°). Maximum length of slope is 12 in (305 mm).
- Dryvit finishes shall not be used below grade when applied as the finish for an EIF system.
- Dryvit finishes are not intended for direct-applied, vertical applications over exterior type gypsum based sheathing board, foam plastic insulation or other type insulation board.
- Dryvit finishes shall not be returned into any sealant joint. Instead, a coat of Dryvit Color Prime™ or Dryvit Demandit® Smooth should be applied over the base coat in the joint.
- Due to the nature of the resins and additives used in the formulation of Weatherlastic finishes, when exposed to damp conditions, the finishes will soften. This property is more pronounced immediately after application; as the finish cures, the degree of softening is reduced.
- Weatherlastic finish colors appear slightly darker than the same color in a Dryvit DPR finish.
- Avoid applying finish in direct sunlight. Always work on the shady side of the wall or protect the area with appropriate shading material.

CLEAN UP

Clean tools with water while the Weatherlastic finish is still wet.

TECHNICAL AND FIELD SERVICES

Available on request.

WEATHERLASTIC® FINISH TESTING

TEST	TEST METHOD	CRITERIA	RESULTS ¹
Surface Burning Characteristics	ASTM E 84	Flame Spread <25 Smoke Developed <450	Passed
Flexibility ²	ASTM D 522 Method B	N/A	Passed: 1.0 in diameter @ 40 °F
Water Vapor Transmission	ASTM E 96 Procedure B	Vapor Permeable	17.4 Perms
Accelerated Weathering	ASTM G 154 Cycle 1 (QUV)	No deleterious effects ³ After 2000 hours	No deleterious effects ³ After 5000 hours
	ASTM G 155 Cycle 1 (Xenon Arc)	No deleterious effects ³ After 2000 hours	No deleterious effects ³ After 5000 hours
Chalk Rating	ASTM D 4214 after ASTM G 154 Cycle 1	N/A	Chalk rating: 9+ after 5000 hours QUV
Instrumentally Measured Color Difference ⁴ (includes yellowing)	ASTM D 2244 CIELAB, 10° Observer after ASTM G 154 Cycle 1	N/A	Color change: 1.3 Delta E after 5000 hours QUV
Freeze-Thaw Resistance	ASTM E 2485	No deleterious effects ³ After 60 cycles	No deleterious effects ³ After 90 cycles
	ASTM E 2485	No deleterious effects ³ After 10 cycles	No deleterious effects ³ After 10 cycles
Mildew Resistance	ASTM D 3273	No growth 28 day during exposure period	No growth after 28 days
Salt Spray Resistance	ASTM B 117	No deleterious effects ³ After 300 hours	No deleterious effects ³ After 1000 hours
Water Resistance	ASTM D 2247	No deleterious effects ³ After 14 days	No deleterious effects ³ After 42 days
Abrasion Resistance	ASTM D 968 Method A Falling Sand	No deleterious effects ³ After 528 quarts (500 liters)	No deleterious effects ³ 1057 quarts (1000 liters)
	ASTM D 4060 Taber Abrasion (500 g load)	N/A	1000 cycles: .50 mg mass loss/rev
Adhesion to Concrete	ASTM D 4541	15 psi minimum	>156 psi
Tensile Bond	ASTM C 297/E 2134	15 psi minimum	>24 psi
Physical Properties ⁵	ASTM D 412	N/A	Tensile Strength 200 psi Elongation – 450% Recovery at 100 % Elongation – 90% minimum

1. Testing referenced is based on Weatherlastic Quarzputz Pastel Base finish.
2. Finish applied over aluminum panels, bent on cylindrical mandrels as described in ASTM D 522 Method B. Lower diameter indicates higher flexibility.
3. No cracking, checking, rusting, crazing, erosion, blistering, peeling, or delamination when viewed under 5x magnification.
4. Delta E is total color difference, including yellowing, lightening, darkening, changes in red, blue, and green color values. Finish exposed to 5,000 hours of QUV prior to evaluating Delta E.
5. These properties are accurate for neat films. Actual results will vary with aggregate size and texture.

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit products as of the date of publication of this document and is presented in good faith. Dryvit assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit.

For more information on Dryvit or Continuous Insulation, [click here](#).

Printed in USA. Issued 1.1.2022
©Dryvit 2022
DS418

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



dryvit.com | 800.556.7752



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com